

Z.M. Muldakhmetov<sup>1</sup>, A.T. Ordabaeva<sup>1\*</sup>, M.G. Meiramov<sup>1</sup>, A.M. Gazaliev<sup>1</sup>,  
Zh.S. Shaikenova<sup>1</sup>, G.K. Mukusheva<sup>2</sup>, T.S. Zhivotova<sup>1</sup>

<sup>1</sup>LLP “Institute of Organic Synthesis and Coal Chemistry of the Republic of Kazakhstan”, Karaganda, Kazakhstan;

<sup>2</sup>Karagandy University of the name of academician E.A. Buketov, Karaganda, Kazakhstan

(\*Corresponding authors e-mail: [aigul\\_serik\\_kz@mail.ru](mailto:aigul_serik_kz@mail.ru))

## Obtaining carbon sorbent from “Euromet” LLP coke breeze

The paper presents the results of a physicochemical analysis of coke sample from “Euromet” LLP (Karaganda, Kazakhstan), which is a carbonaceous material with high carbon content, the absence of volatiles matter and low ash content. Carbon sorbents were obtained from low-value fractions of carbonized materials of the Karaganda region coke production by the steam-gas activation. An important advantage of using screenings (coke breeze class 0-10 mm, which was crushed and fractionated to a particle size of 2-5 mm.) is the exclusion of the energy-intensive carbonization stage from the technological process, which releases a large amount of environmentally harmful substances (phenols, cresols, gaseous emissions etc.). The optimal conditions for obtaining a sorbent from low-value coke breeze are a temperature of 850 °C and an activation time of 2 hours. The physicochemical properties (ash content, bulk density, sorption capacity for iodine and methylene blue, total pore volume for water) of carbon sorbents were determined.

*Keywords:* coke breeze, coals, sorbents, activation, sorption capacity, ash content, burning, bulk density.

### Introduction

Environmental pollution by the oil, coal and metallurgical industries is one of the reasons for the severe environmental consequences and the negative impact on human health. Industrial enterprises of the republic discharge insufficiently treated wastewater into water sources. In addition, the water resources of Kazakhstan are polluted by household and agricultural waste. Currently, there is a tightening of requirements for the standards of discharges and emissions from production and economic activities. The high sorption activity of active carbons determines a wide range of their application, including the possibility of using them for purification from pollutants. The use of this product in the world is steadily growing with the development of industrial production of activated carbon. So in Western Europe, activated carbons are used as the main material for wastewater treatment and gas emissions, in accordance with current environmental regulations. The areas of application of carbon sorbents are inextricably linked both with the knowledge of their sorption properties in relation to various pollutants, and with their physicochemical properties.

Also, in addition to activation gases, various chemical reagents are used at the stages of carbonization and preparation of raw materials. Different vegetable raw materials such as wood, nutshell, remains of stems and seed coats [1, 2], as well as processed carbon-containing substances such as plastics, rubber, oil, coal [3] are used as a raw material for the production of carbon sorbents.

A large amount of low-value fraction (screenings) remains during the preparation products for sale at enterprises producing coke using different technologies. The use of this material will make it possible to obtain highly effective carbon sorbents for the public utilities, chemical, oil, gas, and mining industries with a certain processing.

The advantage of using screenings is the exclusion from the technological process of the energy-consuming carbonization stage, which releases a large amount of environmentally harmful substances (phenols, cresols, gaseous emissions, etc.). It is known that the ash content, bulk density and average particle diameter are linearly related to the degree of burning during activation. However, it is necessary to take into account the specifics of the norms of sorbents for various purposes. Most of them require such parameters as grain size, total pore volume in water, mass fraction of moisture, bulk density, and abrasion resistance.

The grade of coal should be taken into account when activating hard coal [4]. Bituminous coals with a high tar and volatiles content, sinter or swell when heated, and therefore require pre-treatment. Another activation process [5] for coals of the “bituminous C” class with a high content of volatiles and moisture is car-

ried out on grained raw materials, which are first subjected to drying and preliminary oxidation at 150–215 °C. Anthracite, which contains significantly less volatiles, can be activated immediately under appropriate conditions. To do this, anthracite is first crushed, the finely dispersed powder is briquetted with a binder, re-crushed, and after sieving into fractions, it is subjected to carbonization and activation. Direct activation of granular anthracite is difficult to implement and requires a long time in conventional rotary kilns. Low-grade bituminous coals (fat coals) with a relatively high volatile content, which coke poorly and produce grains of low strength, can also be used to produce activated carbons if crushed and washed with dilute mineral acid (hydrochloric, sulfuric or phosphoric). Then after drying, the grains are crushed, the powders are granulated with binders, carbonized and activated [6]. It is possible to activate the products of various stages of molded coke production with gas [7]. Coal-based activated carbons are not produced in Central Kazakhstan. The quality of the finished activated carbon depends on the correctly set technological parameters for the preparation of the initial material, activation modes. At present, the production of activated carbon is promising due to the possibility of obtaining materials with a developed structure for solving various problems, including protection of the biosphere from anthropogenic impact, in nuclear power engineering, and in modern devices for energy storage and transmission. At the same time, the scale of the use of nanoporous carbon is limited by the rather high cost of materials. This leads to the search for new methods for obtaining carbon materials with the required set of properties from cheap types of raw materials, which is an urgent task for science and industry [8]. For example, the cost of adsorbents is 450 times higher than the cost of raw materials with a huge sales market, and the total world production of porous carbon materials is currently about 1 million tons/year [9, 10].

The high rates of development of heavy and light industry, motor transport entail an increasing load on surface waters [11, 12]. The quality of some natural water sources is unacceptable for their use not only for food purposes, but also for technical needs. Hazardous organic substances, heavy metals and radionuclides may be present in water bodies, such water is of poor quality and certainly needs to be cleaned. The use of powdered activated carbon to capture mercury is actual for the Karaganda region (Nura river). In [13], the porous carbon materials obtained from the coal of the Maikuben basin, the Shoptkyol deposit (Kazakhstan), with a specific surface area (348.99 m<sup>2</sup>/g) were tested for the treatment of waste sewage water taken from the SUC “Astana Water Canal” (Nur-Sultan, Kazakhstan). Active carbon is the only type of sorbent that has a high adsorption capacity when extracting toxic organic contaminants from water. All drinking water supply and deep (below maximum permissible concentrations) wastewater treatment are based on the use of powdered and granular activated carbons. For these purposes, 30 % of the global production of activated carbon is spent.

According to experts, it is necessary to produce at least 0.5 kg of activated carbon per capita per year for an environmentally safe and healthy lifestyle of people. This rate is undoubtedly higher in regions with high environmental pollution (for the Republic of Kazakhstan, at least 7.5 thousand tons per year). The main areas of use of carbon sorbents are associated with technological processes of adsorption purification, separation, isolation and concentration in gaseous and liquid media. Volatile organic compounds are the main pollutants of various industrial installations [14–16]. Some volatile organic compounds, such as toluene vapor released into the atmosphere as a result of their use, lead to serious environmental problems, therefore the concentration of which should be reduced to very low levels in the environment [17–19]. Adsorption by activated carbon is one of the most common processes for the removal of volatile organic compounds, especially toluene from gaseous media [20, 21] and phenol from chemical wastewater [22].

In the world market, the main producer of activated carbon is the United States, which accounts for 34 % of the annual production of this product category. Europe, with a share of 24 %, ranks second in terms of activated carbon production. Kazakhstan accounts for only 0.7 % of the global activated carbon production, while Russia accounts for 2 % (Fig. 1).

Demand for activated carbon is growing due to its usefulness as a carbonaceous material in the fight against pollution. As a result, the cost of activated carbon rises depending on the application. The research of scientists is carried out in the direction of searching for a raw material base for the production of activated carbon for its low cost, availability, high carbon content and low ash content. The cost of coke breeze in the Republic of Kazakhstan is 60–90 thousand tenge/t. Activated coals based on coal, depending on the brand, cost from 800 thousand tenge/t. This indicates the need to organize own production facilities for their production.




Figure 1. Share distribution of the annual production of activated carbon by country

The aim of the paper is to determine the possibility of using a low-value fraction of the coke production of “Euromet” LLP (Karaganda, Kazakhstan) as a feedstock for the production of carbon sorbents.

### Experimental

The object of the study was coke breeze of the 0–10 mm class, which was subjected to crushing and fractionation to a particle size of 2–5 mm. Activation of coke from Karaganda coal was carried out on a laboratory unit based on a high-temperature tube furnace with a maximum heating of 1100 °C and a quartz reactor. The amount of steam produced is controlled by the steam generator heater.

To work out the optimal conditions for obtaining active carbon, the feedstock was dried at a temperature of 120 °C for 3 hours, then 150–180 grams were loaded into the reactor, and, after connecting all systems, heating of the furnace was turned on. At 550–700 °C, the components absorbed during the quenching of coke are removed. At a temperature of 800 °C, steam is supplied to the reactor from the steam generator. After reaching the temperature of the set mode, activation continued for 1–2 hours, while the volatile substances condensed in the receiving flask cooled with water, and the resulting gases were removed carbon of the studied coke. The temperature at which the process of interaction of water vapor with the carbon of the coke under study begins was determined using GLC analysis on the “Crystallux 4000 M” (Research and Production Association “MetaKhrom”, Russia) chromatograph. The relative average quadratic change in the output signal for a detector of an accident chromatograph “Crystallux 4000 M” is no more than 2 %. The accuracy of measurement results was estimated using a standard deviation ( $\delta$ ) according to [23, 24]. The correction factor  $T$  is 2.7760 for a 95 % level of reliability (trust probability) of a series of 5 measurements. To calculate the critical value  $F$ , the MS Excel program was used, where regression equations were obtained for the indicators: burnt, ash content, bulk density, sorption capacity for iodine and methylene blue, total pore volume for water, and structural strength.

250–300 g of dry coke with a grain size of 2–5 mm was placed in the reactor, the steam generator was turned on and, after boiling water, the furnace was turned on. Activation temperatures were 750, 800 and 850 °C. The set time for heating the oven to the set temperature was 10 minutes; the duration of activation was 60 and 120 minutes. At the end of the activation time, the heating and steam supply were stopped and, after the reactor cooled down, the yield of the obtained sorbent, the degree of burning, and bulk density were determined. The analysis of the obtained products was carried out according to the procedures [25].

### Results and Discussion

Table 1 shows the main indicators of coke breeze from “Euromet” LLP.

Table 1

#### Indicators of physico-chemical analysis of coke breeze from “Euromet” LLP

The name of indicators	UM	Medium
Mass fraction of carbon, $C^d$	%	upto 84
Ash content on dry state, $A^d$	%	upto 18.0
Mass fraction of total moisture	%	upto 5.0
Structural strength of dry coke	%	78–82

According to the given parameters, coke breeze from the coals of “Euromet” LLP can be used as a raw material for the production of carbon sorbents. Table 2 shows the data and test results from the laboratory of “Coal Research and Development Center” LLP, characterizing the degree of coke activation for the “Euromet” LLP coals in terms of its burning, ash content, bulk density, total pore volume in water, iodine and methylene blue activity.

The boundaries of the confidence interval ( $\pm\Delta$ ) of the measured characteristics of the “Euromet” LLP sorbent, determined taking into account the Student's criterion, are given in Tables 2 and 3.

Table 2

**Conditions for obtaining and characteristics of the “Euromet” LLP sorbent**

The mode for sorbent obtaining		Combustion loss, %	Ash content, %	Bulk density, g/dm <sup>3</sup>
T, °C	duration of activation, hour			
750	2	20.71±0.63	23.33±0.49	330±4.5
800	1	20.90±0.32	24.04±0.50	333±4.3
800	2	22.00±0.42	24.75±0.51	335±4.2
850	1	23.11±0.49	25.78±0.54	338±3.9
850	2	34.76±0.49	29.82±0.45	339±3.8

Table 3

**Conditions for obtaining and characteristics of the «Euromet» LLP sorbent**

The mode for sorbent obtaining		Sorption capacity		Total pore volume by water, cm <sup>3</sup> /g	Structural strength, %
T, °C	duration of activation, hour	for iodine, %	Methylene blue, mg/g		
750	2	22.50±0.41	55±0.9	0.5258±0.0102	9.50±0.115
800	1	23.05±0.53	50±1.1	0.3533±0.0089	9.40±0.207
800	2	24.20±0.58	20±1.2	0.5975±0.0081	9.70±0.158
850	1	25.50±0.60	100±1.4154	0.5711±0.0167	9.60±0.207
850	2	27.94*±0.63	130±1.4	0.7501*±0.0086	9.80*±0.158

For the combustion loss index, the regression equation with different variations in the temperature and time modes of coal processing (Table 2) is described by the following equation:

$$Y (\text{combustion loss}) = 0.1244T + 9.32t - 92.34. \quad (1)$$

The coefficient of determination R-square is 0.83, the critical value F is 5.03, which is greater than the significance criterion F, equal to 0.16, which confirms the significance of the burn value from the mode of obtaining the sorbent. From equation (1) it follows that the amount of combustion loss increases linearly with increasing temperature and duration of the process.

The regression equation for the ash content index from the temperature and time modes of coal processing (Table 2) is described by the following equation:

$$Y (\text{ash content}) = 0.030902T + 3.00523t - 3.923233. \quad (2)$$

In this case, the value of R-square is 0.15, the critical value of F is 0.18, which is less than the significance criterion F, equal to 0.84, which indicates the significance of the value of the composition of the initial coal, but does not depend on the mode of its processing. Analysis of equations (2) shows that the ash content depends on the temperature and duration of the process, due to a decrease in the mass fraction of carbon.

The regression equation linking the obtained indicators for bulk density with different variations in the temperature and time modes of coal processing (Table 2) is as follows:

$$Y (\text{bulk density}) = 0.144T + 1.4t - 471.4. \quad (3)$$

The value of the R-square is 0.03, and the critical value F 0.03 is less than the significance criterion F 0.96, which also indicates the significance of the value of the composition of the initial coal, but does not depend on the processing mode. An analysis of equation (3) shows that the bulk density value slightly depends on the process temperature and increases with the length of the processing time.

A regression equation has been obtained that relates the obtained indicators for the iodine sorption capacity with different variations in the temperature and time modes of coal processing (Table 3):

$$Y (\text{sorption capacity for iodine}) = 0.05332T + 1.938t - 21.652. \quad (4)$$

The R-square value is 0.96, the critical value F 25.19 is greater than the significance criterion F 0.03, which indicates the significance of the indicator from the mode of obtaining the sorbent.

A regression equation was obtained that relates the obtained indicators for the sorption capacity for methylene blue with different variations in the temperature and time modes of coal processing (Table 3):

$$Y (\text{sorption capacity for methylene blue}) = 0.8T + 13.33t - 598.333. \quad (5)$$

The value of the R-square is 0.53, the critical value F 1.36 is greater than the significance criterion F 0.46, which indicates the significance of the indicator from the mode of obtaining the sorbent.

A regression equation has been obtained that relates the obtained indicators for the total pore volume in water with different variations in the temperature and time regimes of coal processing (Table 3):

$$Y (\text{total pore volume by water}) = 0.002666T + 0.228907t - 1.96583. \quad (6)$$

The R-square value is 0.93, the critical value F 13.68 is greater than the significance criterion F 0.06, which indicates the significance of the indicator from the mode of obtaining the sorbent.

A regression equation has been obtained that relates the obtained indicators for structural strength with different variations in the temperature and time modes of coal processing (Table 3):

$$Y (\text{structural strength}) = 0.0032T + 0.246667t - 6.613333. \quad (7)$$

The R-square value is 0.97, the critical value F 36.5 is greater than the significance criterion F 0.02, which indicates the significance of the indicator from the mode of obtaining the sorbent.

Equations (4–7) show that the contribution of temperature to the increase in sorption capacity is significant for the indicator of sorption capacity for iodine and methylene blue, and for indicators of the total pore volume for water and structural strength, which will allow us to conclude that macropores in the sorbent increase. The value of the sorption capacity for iodine increases with increasing temperature treatment, which is consistent with theoretical ideas about the process.

Methylene blue activity gives an idea of the AC surface formed by pores larger than 1.5 nm, since the indicator molecule is relatively large. Therefore, low activity indicators for iodine, which is adsorbed on the surface of pores with a diameter significantly more than 1 nm, and methylene blue are not an indicator of the low quality of the carbon sorbent [26]. With a large specific surface, the proportion of thin pores increases, which do not fit large molecules, for example, persistent organic pollutants such as phenols, aromatic and polyaromatic hydrocarbons, etc. The results of sorption activity for iodine (MRTU No6-16-1003-67) [27] and clarifying ability for methylene blue (GOST 4453–74) [28] showed that the optimal conditions for obtaining a sorbent from coke breeze are: temperature 850 °C and activation time 2 hours. Properties activated carbons depend on the choice of the appropriate raw material, method and activation conditions. At the same time, a number of conditions can affect certain properties. Thus, the number and distribution of pore sizes depend, in particular, on the nature of the raw material, the type and conditions of the activation process. The formation of gaseous products (H<sub>2</sub>, CO, CO<sub>2</sub>, CH<sub>4</sub>) begins at a temperature of 670<sup>0</sup>C, which indicates the presence of water vapor with the carbon of coke breeze.

It is established that the exhaust gas contains hydrogen, carbon dioxide, methane and carbon monoxide. When carbon interacts with water vapor or carbon dioxide, the following reactions occur simultaneously (Equations 8–10):





Table 4 shows the composition of gases obtained during the activation of coke breeze of “Euromet” LLP.

The composition of the gas obtained during the activation of “Euromet” LLP coke breeze

Gas	Gas outlet mode							
	T, °C		τ, min		T, °C		τ, min	
	670	120	750	120	800	120	850	120
H <sub>2</sub>	50.33		55.23		59.08		53.7	
O <sub>2</sub>	–		–		–		–	
N <sub>2</sub>	0.780		0.80		0.95		0.95	
CO <sub>2</sub>	18.90		20.40		15.43		10.74	
CH <sub>4</sub>	3.35		3.05		3.38		0.89	
CO	17.42		20.52		21.16		33.72	

Thus, a carbon sorbent with a high adsorbing property was obtained as a result of the high-temperature process of activation of coke breeze with water vapor on the basis of “Euromet” LLP (Karaganda, Kazakhstan) coal.

### Conclusions

Physical and chemical analyzes showed that a sample of coke breeze from «Euromet» LLP (Karaganda, Kazakhstan) is a highly active carbonaceous material with a high carbon and low ash content. The optimal technological parameters for obtaining carbon sorbents from screenings of coke production at a laboratory facility (temperature 850°C and activation time 2 hours) were established. The conditions for coke breeze activation and characteristics (combustion loss, ash content, bulk density, total pore volume in water and activity in terms of iodine and methylene blue) of the obtained sorbent were determined.

### Acknowledgements

The study was funded by the Science Committee of the Ministry of Education and Science of the Republic of Kazakhstan under program No. BR10965230.

### References

- 1 Imran Ali, Mohd. Asim. Low cost adsorbents for the removal of organic pollutants from wastewater / Imran Ali, Mohd. Asim, Tabrez A.Khan. // Journal of Environmental Management. — 2012. — Vol. — 113. — P. 170–183. <https://doi.org/10.1016/j.jenvman.2012.08.028>
- 2 Sabino De Gisi, GiusyLofrano. Characteristics and adsorption capacities of low-cost sorbents for wastewater treatment: A review / Sabino De Gisi, GiusyLofrano, Mariangela Grassi, Michele Notarnicola // Sustainable Materials and Technologies. — 2016. — Vol. 9. — P. 10–40. <https://doi.org/10.1016/j.susmat.2016.06.002>
- 3 Geoffrey S. Simatea. Coal-based adsorbents for water and wastewater treatment / Geoffrey S.Simatea, Nthabiseng Maledia, AoyiOchieng, SehlieloNdlovua, Jun Zhangd, Lubinda F. Walubitaie // Journal of Environmental Chemical Engineering. — 2016. — Vol. 4, No. 2. — P. 2291–2312. <https://doi.org/10.1016/j.jece.2016.03.051>
- 4 Еремин И.В. Марочный состав углей и их рациональное использование / И.В. Еремин, Т.М. Броновец. — М.: Недра, 1994. — 268 с.
- 5 Камнева А.И. Химия горючих ископаемых / А.И. Камнева. — М.: Химия, 1974. — 271 с.
- 6 Штах Э. Петрология углей / Э. Штах, М.Т. Маковский, М. Тейхмоллер. — М.: Мир, 1973. — С. 54–96.
- 7 Кельцев Н.В. Основы адсорбционной техники / Н.В. Кельцев. — М.: Химия, 1984. — 592 с.
- 8 Хабибуллин Е.Р. Комплексное исследование каменных углей Кузбасса ряда метаморфизма / Е.Р. Хабибуллин, З.Р. Исмагилов, Н.В. Журавлева, С.А. Созинов, С.Ю. Лыршиков, Р.И. Фурега, Л.М. Хицова, Р.Р. Потоккина // VII Международный Российско-Казахстанский симпозиум «Углекимия и экология Кузбасса». — Кемерово: ФИЦ УУХ СО РАН, 2018. — С. 99.
- 9 Ермагамбет Б.Т. Электрофизические свойства и теплоемкость сланца Кендырлыкского месторождения / Б.Т. Ермагамбет, Б.К. Касенов, Н.У. Нургалиев, М.А. Набиев, Ж.М. Касенова, М.К. Казанкапова, А.М. Зикирина // Химия твердого топлива. — 2018. — № 1. — С. 68–72. <https://doi.org/10.7868/S0023117718010127>
- 10 Ермагамбет Б.Т. Получение адсорбента из горючего сланца Кендырлыкского месторождения / Б.Т. Ермагамбет, Б.К. Касенов, Н.У. Нургалиев, М.К. Казанкапова, Ж.М. Касенова, А.М. Зикирина // Химия твердого топлива. — 2018. — № 5. — С. 27–32. <https://doi.org/10.1134/S0023117718050043>
- 11 Берлинтейгер Е.С. Изучение основных видов загрязнений водных ресурсов Кузбасса / Е.С. Берлинтейгер // Международный журнал прикладных и фундаментальных исследований. — 2013. — № 11–1. — С. 55.

- 12 Wang Guofa. Intelligent and ecological coal mining as well as clean utilization technology in China: Review and prospects / Wang Guofa, Xu Yongxiang, Ren Huaiwei // International Journal of Mining Science and Technology. — 2018. — Vol. 9. — P. 54–62. <https://doi.org/10.1016/j.ijmst.2018.06.005>
- 13 Ермагамбет Б.Т. Электрофизические свойства и теплоемкость пористо-углеродного материала из угля Майкубенского бассейна / Б.Т. Ермагамбет, Б.К. Касенов, М.К. Казанкапова, Н.У. Нурғалиев, Ж.М. Касенова, Е.Е. Куанышбеков, А.Т. Наурызбаева // Химия твердого топлива. — 2020. — № 3. — С. 61–67. <https://doi.org/10.31857/S0023117720030032>
- 14 Singh K. Biofiltration of toluene using wood charcoal as the biofilter media / Singh K., Singh R.S., Rai B.N. and Upadhyay S.N. // Bioresource Technology. — 2010. — Vol. 101, No. 11. — P. 3947–3951. <https://doi.org/10.1016/j.biortech.2010.01.025>
- 15 Mathur A.K. Combined removal of BTEX in air steam by using mixture of sugar cane bagasse, compost and GAC as biofilter media / A.K. Mathur, C.B. Majumber, S. Chatterjee // Journal of Hazardous Materials. — 2007. — Vol. 148, No. 1–2. — P. 64–74. <https://doi.org/10.1016/j.jhazmat.2007.02.030>
- 16 Farhadian M. In situ bioremediation of monoaromatic pollutants in groundwater: a review / M. Farhadian, C. Vachelard, D. Duchez, C. Larroche // Bioresource Technology. — 2008. — Vol. 99, No. 13. — P. 5296–5308. <https://doi.org/10.1016/j.colsurfa.2009.10.025>
- 17 Su F. Adsorption of benzene, toluene, ethylbenzene and p-xylene by NaOCl — oxidized carbon nanotubes / Su F., Lu C., and Hu S. // Colloids and Surfaces A. — 2010. — Vol. 353, No. 1. — P. 83–91. <https://doi.org/10.1016/j.colsurfa.2009.10.025>
- 18 Nourmoradi H. Removal of benzene, toluene, ethylbenzene and xylene (BTEX) from aqueous solutions by montmorillonite modified with nonionic surfactant: equilibrium, kinetic and thermodynamic study / Nourmoradi H., Nikaeen M. and Nejad M.H. // Chemical Engineering Journal. — 2012. — Vol. 191. — P. 341–348. <https://doi.org/10.1016/j.cej.2012.03.029>
- 19 Yang C. nBiomass accumulation and control strategies in gas biofiltration / Yang C., Chen H., Zeng G., Yu G. and Luo S. // Biotechnology Advances. — 2010. — Vol. 28, No. 4. — P. 531–540. <https://doi.org/10.1016/j.biotechadv.2010.04.002>
- 20 Pei J. Determination of adsorption isotherm and diffusion coefficient of toluene on activated carbon at low concentrations / Pei J. and Zhang J.S. // Building and Environment. — 2012. — Vol. 48. — P. 66–76. <https://doi.org/10.1016/j.buildenv.2011.08.005>
- 21 Kim K.D., Effect of thin hydrophobic films for toluene adsorption and desorption behavior on activated carbon fiber under dry and humid conditions / Kim K. D., Park E. J., Seo H. O., Jeong M.G., Kim Y.D. and Lim D.C. // Chemical Engineering Journal. — 2012. — Vol. 200–202. — P. 133–139. <https://doi.org/10.1016/j.cej.2012.06.044>
- 22 Тамаркина Ю.В. Адсорбция фенола активированными углями на основе ископаемых углей разной степени метаморфизма / Тамаркина Ю.В., Анищенко В.Н., Редько А.Н., Кучеренко В.А. // Химия твердого топлива. — 2021. — № 3. — С. 3–11. <https://doi.org/10.31857/S0023117721030105>
- 23 Акегян Т.А. Основы теории ошибок / Т.А. Акегян. — М.: Наука, 1972. — 170 с.
- 24 Гордон А. Спутник химика / А. Гордон, Р. Форд. — М.: Наука, 1976. — 541 с.
- 25 Колышкин Д.А. Активные угли. Свойства и методы испытаний / Д.А. Колышкин, К.К. Михайлова. — М.: Химия, 1972. — С. 52–54.
- 26 Кинле Х. Активные угли и их промышленное применение / Х. Кинле, Э. Бадер. — Л.: Химия, 1984. — 216 с.
- 27 МРТУ № 6-16-1003-67. Активные угли. Методы испытаний. Метод определения сорбционной активности по йоду.
- 28 ГОСТ 4453-74. Уголь активный осветляющий древесный порошкообразный. Технические условия. — Взамен ГОСТ 4453-48; Введ. с 01.01.76 по 01.01.96. — М.: Изд-во стандартов, 1993. — 23 с.

З.М. Молдахметов, А.Т. Ордабаева, М.Г. Мейрамов, А.М. Ғазалиев,  
Ж.С. Шайкенова, Г.К. Мұқышева, Т.С. Животова

### «Евромет» ЖШС Кокс ұнтағынан көміртекті сорбент алу

Жұмыста «Евромет» ЖШС (Қарағанды қ.) кокс ұнтағынан үлгісін физика-химиялық талдау нәтижелері келтірілген, ол құрамында көміртегі жоғары, ұшпа және күлділігі төмен көміртекті материал болып табылады. Көміртекті сорбенттер Қарағанды облысының кокс-химия өндірісінің карбонизацияланған материалдарының аз ликвидті фракцияларынан бу-газды активтендіру әдісімен алынды. Қалдықтарды пайдаланудың маңызды артықшылығы (ұсақтауға және 2–5 мм-ге дейін фракциялауға ұшыраған 0–10 мм класты кокс ұсақтары) технологиялық процестен экологиялық зиянды заттардың көп мөлшері (фенолдар, крезолдар, газ тәрізді шығарындылар және т.б.) шығарылатын карбонизацияның энергияны ысырап ететін сатысын алып тастау болып табылады. Аз ликвидті кокс ұнтағынан сорбент алудың оңтайлы шарттары активтендіру уақыты 2 сағат болған кезде 850 °С температура болып табылады. Көміртегі сорбенттерінің физика-химиялық қасиеттері (күл, сусымалы тығыздық, йод және метилен көк бойынша сорбциялық сыйымдылық, су бойынша кеуектердің жиынтық көлемі) анықталды.

*Кілт сөздер:* кокстыұсақ-түйек, көмір, сорбенттер, активтендіру, сорбциялықсыйымдылық, күлділік, күйдіру, үйілмелітығыздық.

З.М. Мулдахметов, А.Т. Ордабаева, М.Г. Мейрамов, А.М. Газалиев,  
Ж.С. Шайкенова, Г.К. Мукушева, Т.С. Животова

## Получение углеродного сорбента из коксовой мелочи ТОО «Евромет»

В работе приведены результаты физико-химического анализа образца коксовой мелочи ТОО «Евромет» (г. Караганда), представляющего собой углеродистый материал с высоким содержанием углерода, отсутствием летучих веществ и низкой зольностью. Углеродные сорбенты были получены из малоликвидных фракций карбонизованных материалов коксохимического производства Карагандинской области методом парогазовой активации. Важным преимуществом использования отсеков (коксовая мелочь класса 0–10 мм, которая подвергалась дроблению и фракционированию до крупности 2–5 мм) является исключение из технологического процесса энергозатратной стадии карбонизации, при которой выделяется большое количество экологически вредных веществ (фенолы, крезолы, газообразные выбросы и т.д.). Оптимальными условиями получения сорбента из малоликвидной коксовой мелочи являются температура 850<sup>0</sup>С при времени активации 2 часа. Определены физико-химические свойства (зольность, насыпная плотность, сорбционная емкость по йоду и по метиленовому голубому, суммарный объем пор по воде) углеродных сорбентов.

*Ключевые слова:* коксовая мелочь, угли, сорбенты, активация, сорбционная емкость, зольность, обгар, насыпная плотность.

### References

- 1 Ali, I., Asim, M., AKhan, T. (2012). Low cost adsorbents for the removal of organic pollutants from wastewater. *Journal of Environmental Management*, 113, 170–183. <https://doi.org/10.1016/j.jenvman.2012.08.028>
- 2 De Gisi, S., Lofrano, G., Grassi, M., & Notarnicola, M. (2016). Characteristics and adsorption capacities of low-cost sorbents for wastewater treatment: A review. *Sustainable Materials and Technologies*, 9, 10–40. <https://doi.org/10.1016/j.susmat.2016.06.002>
- 3 Simatea, G.S., Maledia, N., Ochiengc, A., Ndlovua, S., Zhangd, J., & Walubita, L.F. (2016). Coal-based adsorbents for water and wastewater treatment. *Journal of Environmental Chemical Engineering*, 4(2), 2291–2312. <https://doi.org/10.1016/j.jece.2016.03.051>
- 4 Yeremin, I.V., & Bronovets, T.M. (1994). Marochnyy sostav ugley i ikh ratsional'noye ispol'zovaniye [Grade composition of coals and their rational use]. Moscow: Nedra [in Russian].
- 5 Kamneva, A.I. (1974). Khimiia goriuchikh iskopaemykh [Chemistry of fossil fuels]. Moscow: Chemistry [in Russian].
- 6 Shtakh, E., Makovsky, M.T., & Teykhmolleridr M. (1973) Petrologiia ugley [Petrology of coals]. Moscow: Mir [in Russian].
- 7 Kel'tsev, N.V. (1984). Osnovy adsorbtsionnoy tekhniki [Fundamentals of adsorption technology]. Moscow: Khimiia [in Russian].
- 8 Xabibullin, E.R., Ismagilov, Z.R., Zhuravleva, N.V., Sozinov, S.A., Ly`rshhikov, S.Yu., Furega., R.I., Xiczova, L.M., & Potokina, R.R. (2018). Kompleksnoe issledovanie kamenny`x ugley Kuzbassa ryada metamorfizma [Comprehensive study of coals of Kuzbass of a series of metamorphism]. VII Mezhdunarodny`j Rossijsko-Kazaxstanskij simpozium «Ugleximiya i e`kologiya Kuzbassa», Kemerovo: FICz UUX SO RAN. 99.
- 9 Ermagambet, B.T., Kasenov, B.K., Nurgaliev, N.U., Nabiev, M.A., Kasenova, Zh.M., Kazankapova, M.K., & Zikirina, A.M. (2018). E`lektrofizicheskie svojstva I teploemkost` slanca Kendy`rly`kskogo mestorozhdeniya [Electrophysical properties and heat capacity of shale from the Kendyrylk deposit]. *Ximiya tverdogo topliva*, 1, 68–72. <https://doi.org/10.7868/S0023117718010127>
- 10 Ermagambet, B.T., Kasenov, B.K., Nurgaliev, N.U., Kazankapova, M.K., Kasenova, Zh.M., & Zikirina, A.M. (2018). Poluchenie adsorbenta iz goryuchego slanca Kendy`rly`kskogo mestorozhdeniya [Obtaining an adsorbent from oil shale of the Kendyrylk deposit]. *Ximiya tverdogo topliva*, 5, 27–32. <https://doi.org/10.1134/S0023117718050043>
- 11 Berlinteyger, Ye.S. (2013). Izucheniye osnovnykh vidov zagryaneniya vodnykh resursov Kuzbassa. *Mezhdunarodnyy zhurnal prikladnykh I fundamental'nykh issledovaniy*, 11-1, 55 [in Russian].
- 12 Wang, G., Xu, Y., & Huaiwei, R. (2018). Intelligent and ecological coal mining as well as clean utilization technology in China: Review and prospects. *International Journal of Mining Science and Technology*, (9), 54–62. <https://doi.org/10.1016/j.ijmst.2018.06.005>
- 13 Ermagambet, B.T., Kasenov, B.K., Kazankapova, M.K., Nurgaliev, N.U., Kasenova, Zh.M., Kuany`shbekov, E.E., & Naury`zbaeva, A.T. (2020). E`lektro fizicheskie svojstva I teploemkost` poristo-uglerodnogo materiala iz uglya Majkubenskogo bassejna. *Ximiya tverdogo topliva*. 3, 61–67. <https://doi.org/10.31857/S0023117720030032>
- 14 Singh, K., Singh, R.S., Rai, B.N., & Upadhyay, S.N. (2010). Biofiltration of toluene using wood charcoal as the biofilter media. *Bioresource Technology*, 101(11), 3947–3951. <https://doi.org/10.1016/j.biortech.2010.01.025>
- 15 Mathur, A.K., Majumber, C. B., & Chatterjee, S. (2007). Combined removal of BTEX in air steam by using mixture of sugar cane bagasse, compost and GAC as biofilter media. *Journal of Hazardous Materials*. 148(1-2), 64–74. <https://doi.org/10.1016/j.jhazmat.2007.02.030>



- 16 Farhadian, M., Vachelard, C., Duchez, D., & Larroche, C. (2008). In situ bioremediation of monoaromatic pollutants in groundwater: a review. *Bioresource Technology*, 99(13), 5296–5308. <https://doi.org/10.1016/j.colsurfa.2009.10.025>
- 17 Su, F., Lu C., & Hu, S. (2010). Adsorption of benzene, toluene, ethylbenzene and pxylene by NaOCl — oxidized carbon nanotubes. *Colloids and Surfaces A*. 353(1), 83–91. <https://doi.org/10.1016/j.colsurfa.2009.10.025>
- 18 Nourmoradi, H., Nikaen, M & Nejad, M.H. (2012). Removal of benzene, toluene, ethylbenzene and xylene (BTEX) from aqueous solutions by montmorillonite modified with nonionic surfactant: equilibrium, kinetic and thermodynamic study. *Chemical Engineering Journal*, (191), 341–348. <https://doi.org/10.1016/j.cej.2012.03.029>
- 19 Yang, C., Chen, H., Zeng, G., Yu, G. & Luo, S. (2010). Biomass accumulation and control strategies in gas biofiltration. *Biotechnology Advances*, 28(4), 531–540. <https://doi.org/10.1016/j.biotechadv.2010.04.002>
- 20 Pei, J. & Zhang, J.S. (2012). Determination of adsorption isotherm and diffusion coefficient of toluene on activated carbon at low concentrations. *Building and Environment*, 48(66–76). <https://doi.org/10.1016/j.buildenv.2011.08.005>
- 21 Kim, K.D., Park, E.J., Seo, H.O., Jeong, M.G., Kim, Y.D. & Lim, D.C. (2012). Effect of thin hydrophobic films for toluene adsorption and desorption behavior on activated carbon fiber under dry and humid conditions. *Chemical Engineering Journal*, 200–202, 133–139. <https://doi.org/10.1016/j.cej.2012.06.044>
- 22 Tamarkina, Yu.V., Anishhenko, V.N., Red'ko, A.N., Kucherenko, V.A. (2021). Adsorbciya fenola aktivirovanny`m iuglyam i na osnove iskopaemy`x uglejraznoj stepeni metamorfizma. *Ximiya tverdogo topliva*, 3, 3–11. <https://doi.org/10.31857/S0023117721030105>
- 23 Akegyan, T.A. (1972). *Osnovy` teoriioshibok* [Fundamentals of error theory]. Moscow: Nauka [in Russian].
- 24 Gordon, A., Ford, R. (1976). *Sputnik ximika* [Chemist's companion]. Moscow: Nauka [in Russian].
- 25 Kolyshkin, D.A., & Mikhaylova, K.K. (1972). *Aktivnyye ugli. Svoystva i metodyispytaniy*. Moscow: Khimiia [in Russian].
- 26 Kinle, K.H., & Bader, E. (1984). *Aktivnyye ugli i ikh promyshlennoye primeneniye* [Active coals and their industrial application]. Leningrad: Khimiia [in Russian].
- 27 MRTU № 6-16-1003-67. (1967). *Aktivnyeugli. Metodyispytaniy. Metod opredeleniia sorbtionnoi aktivnosti po iodu* [Active coals. Test methods. Method for determination of sorption activity by iodine] [in Russian].
- 28 GOST 4453-74. (1993) *Ugol aktivnyi osvetliayushchii drevesnyi poroshkoobraznyi. Tekhnicheskie usloviia*. [Charcoal active brightening wood powder. Specifications.] *Vzamen GOST 4453-48*; Vved. s 01.01.76 po 01.01.96. Moskva: Izd-vo standartov. 23 p. [in Russian].

#### Information about authors

**Muldakhmetov, Zeynulla Muldakhmetovich** — Doctor of Chemical Sciences, Academician, Director of the Institute, Institute of Organic Synthesis and Coal Chemistry, Alikhanov str. 1, 100008, Karaganda, Kazakhstan; e-mail: [zmm\\_ioscc@mail.ru](mailto:zmm_ioscc@mail.ru); <https://orcid.org/0000-0001-9497-2545>;

**Ordabaeva, Aigul Tanirbergenovna** — Candidate of chemical sciences, head of the Laboratory of Coal Chemistry, Institute of Organic Synthesis and Coal Chemistry, Alikhanov str. 1, 100008, Karaganda, Kazakhstan; e-mail: [aigul\\_serik\\_kz@mail.ru](mailto:aigul_serik_kz@mail.ru); <https://orcid.org/0000-0002-4413-1163>;

**Meiramov, Mazhit Gabdullovich** — Candidate of chemical sciences, Institute of Organic Synthesis and Coal Chemistry, Alikhanov str. 1, 100008, Karaganda, Kazakhstan; e-mail: [majit\\_m@mail.ru](mailto:majit_m@mail.ru); <https://orcid.org/0000-0003-2498-6516>;

**Gazaliev, Arstan Maulenovich** — Doctor of Chemical Sciences, Academician, Deputy Director for Science of the Institute, Institute of Organic Synthesis and Coal Chemistry, Alikhanov str. 1, 100008, Karaganda, Kazakhstan; e-mail: [gazaliyev51@mail.ru](mailto:gazaliyev51@mail.ru); <https://orcid.org/0000-0003-2161-0329>;

**Shaikenova, Zhazira Sergalievna** — Researcher, Master of Biological Sciences, Institute of Organic Synthesis and Coal Chemistry, Alikhanov str. 1, 100008, Karaganda, Kazakhstan; e-mail: [plant-2019@mail.ru](mailto:plant-2019@mail.ru); <https://orcid.org/0000-0001-8440-6056>;

**Mukusheva, Gulim Kenesbekovna** — Candidate of chemical sciences, Associated Professor, Karaganda University of the name of academician E.A. Buketov, Universitetskaya str., 28, 100024, Karaganda, Kazakhstan; e-mail: [mukusheva1977@list.ru](mailto:mukusheva1977@list.ru); <https://orcid.org/0000-0001-6706-4816>;

**Zhivotova, Tatyana Sergeevna** — Doctor of Chemical Sciences, Chief Scientific Secretary of the Institute, Institute of Organic Synthesis and Coal Chemistry, Alikhanov str. 1, 100008, Karaganda, Kazakhstan; e-mail: [zhts2004@mail.ru](mailto:zhts2004@mail.ru); <https://orcid.org/0000-0002-0793-4653>